

### 試驗報告

報告編號: TB-21-02369  
C-21-06146  
頁數: 2 OF 2  
報告日期: 110年05月14日

#### 試驗結果:

試驗項目	試驗結果	方法偵測極限(MDL)	試驗方法
甲磁釋出量-最大值 (mg/L)	< 0.2 (0.1)	0.05	CNS 1349(2014)
甲磁釋出量-平均值 (mg/L)	< 0.2 (0.1)	0.05	

註: 1. 試驗樣品厚度為 17.5 mm  
2. 試驗結果低於方法偵測極限值(MDL)之測定值以"N.D."表示;  
若高於方法偵測極限值(MDL), 但低於定量極限值(QDL)時, 以"<0.2"表示,  
並括號註明其實測值  
3. N.D. = Not Detected / 未檢出  
4. 本試驗報告之試驗地點同實驗室地址

-----000-----

### 試驗報告

報告編號: TB-21-02369  
C-21-06146  
頁數: 1 OF 2  
報告日期: 110年05月14日

工程名稱: 自測  
委託單位: 三朋行股份有限公司  
供料廠商: 三朋行股份有限公司  
取樣名稱: 木心板型號:SBH-101, 厚度:17.5 mm, 層數:5層  
送驗人員: 三朋行股份有限公司-歐怡伶  
收試日期: 110年04月28日  
備註: 1. 以上資料由顧客提供(收件及試驗日期除外)  
2. 除非另有說明, 此報告結果僅對測試之樣品負責  
3. 未經本公司事先書面同意, 此報告不可部分複製  
3. 下述報告內容標示#處由顧客提供

#### 試驗結果:

試驗項目	試驗結果	試驗方法
氣乾密度 (g/cm <sup>3</sup> )	0.33	CNS 1349(2014)

本報告若有提供規範值時, 該規範僅供參考, 合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/terms-and-conditions> and for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/terms-and-conditions>. Attention is drawn to the limitation of liability and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this combined document reflects the Company's findings at the time of its intervention only and shall not be used for any other purpose. The Company cannot be held responsible for reproduction of this document without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the transmission documents, this document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the transmission documents, this document is invalid and clients may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd. No. 8, Mah Rd, Taichung Industrial Park, Taichung 40755, Taiwan / 40755 台中市工業區14路89號  
T: (886) 41 2359 2597 www.sgs.com.tw

報告編號: TB-21-02369  
C-21-06146  
頁數: 1 OF 2  
報告日期: 110年05月14日

工程名稱: 自測  
委託單位: 三朋行股份有限公司  
供料廠商: 三朋行股份有限公司  
取樣名稱: 木心板型號:SBH-101, 厚度:17.5 mm, 層數:5層  
送驗人員: 三朋行股份有限公司-歐怡伶  
收試日期: 110年04月28日  
備註: 1. 以上資料由顧客提供(收件及試驗日期除外)  
2. 除非另有說明, 此報告結果僅對測試之樣品負責  
3. 未經本公司事先書面同意, 此報告不可部分複製  
3. 下述報告內容標示#處由顧客提供

#### 試驗結果:

試驗項目	試驗結果	試驗方法
氣乾密度 (g/cm <sup>3</sup> )	0.33	CNS 1349(2014)

本報告若有提供規範值時, 該規範僅供參考, 合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/terms-and-conditions> and for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/terms-and-conditions>. Attention is drawn to the limitation of liability and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this combined document reflects the Company's findings at the time of its intervention only and shall not be used for any other purpose. The Company cannot be held responsible for reproduction of this document without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the transmission documents, this document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the transmission documents, this document is invalid and clients may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

SGS Taiwan Ltd. No. 8, Mah Rd, Taichung Industrial Park, Taichung 40755, Taiwan / 40755 台中市工業區14路89號  
T: (886) 41 2359 2597 www.sgs.com.tw



Testing Laboratory  
0292

材料暨工程實驗室-台中

## 試驗報告



報告編號：TB-23-06903  
C-23-16696

頁數：1 OF 1  
報告發行日期：112年12月12日


工程名稱：自測  
承包商：-----  
委託單位：三朋行股份有限公司  
供料廠商：三朋行股份有限公司  
樣品名稱：木心板,SBH-101,厚17.5mm  
取樣人員：三朋行股份有限公司-陳怡伶  
送驗人員：三朋行股份有限公司-陳怡伶  
收件日期：112年11月30日  
試驗日期：112年11月30日~112年12月12日  
備註：1.以上資料(會驗人員、試驗方法、試驗數量、收件日期及試驗日期除外)及下述報告內容標示#處係由顧客提供  
2.除非另有說明，此報告結果僅適用於收取之試驗件  
未經本公司事先書面同意，此報告不可部分複製

### 試驗結果：

試驗項目	試驗結果	方法偵測極限(MDL)	試驗方法
甲醛釋出量-最大值 (mg/L)	0.3	0.05	CNS 1349:2014
甲醛釋出量-平均值 (mg/L)	0.3	0.05	

- 註：1.試驗結果若低於方法偵測極限值(MDL)之測定值以"N.D."表示；  
若高於方法偵測極限值(MDL)，但低於定量極限值(QDL)時，以"<0.2"表示，  
並括號註明其實測值，定量極限值(QDL)為 0.2 mg/L  
2.N.D. = Not Detected / 未檢出  
3.樣品描述：普通合板  
4.本實驗室執行試驗之地點同實驗室地址

----- oOo -----

  
報告簽署人

本報告若有提供規範值時，該規範值僅供參考，合格之判定以委託單位實際要求為準

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com.tw/Terms-and-Conditions> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com.tw/Terms-and-Conditions>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.



## 綠建材標章證書

綠建材標章證書字號：GBM0103487(續)

申請廠商：三朋行股份有限公司  
申請人：薛仁一  
廠商地址：嘉義縣民雄鄉北斗村成功一街 11 號  
產品名稱：防蟲木心板  
產品型號：SBH-101(厚度 17.5mm, 5 層, F1)  
SBH-102(厚度 15mm, 5 層, F1)、  
SBH-103(厚度 17.2mm, 5 層, F1)  
生產廠址：嘉義縣民雄鄉北斗村成功一街 11 號  
有效期限：自 113 年 12 月 1 日至 117 年 11 月 30 日止  
合格項目：健康綠建材 (E2 逸散)  
試驗項目：甲醛 (HCHO) 逸散速率  
總揮發性有機物質 (TVOC) 逸散速率

內政部 部長

劉世芳

中華民國 113 年 10 月 4 日

